

Walkways, escape routes and lay down areas

### Typical systems

Pre-qualifications tested according to Edition 5 of NORSOK M-501 are still valid as the coating systems also fulfil all requirements in Edition 6.

Other options are available- contact TSS

System no.	Surface preparation	Coating system	DFT $\mu\text{m}$	Test report number
4-1	Sa 2½	Baltoflake Baltoflake Baltoflake – Carborex - Baltoflake	750 750 <u>600</u> <b>2100</b>	410-02-0013 M13
4-2	Sa 2½	Jotamastic 80, alum. Jotamastic 80, alum. Jota Armour	150 150 <u>1000</u> <b>1300</b>	3410-10-0014 Mt06
4-3	Sa 2½	Jotamastic 80 WG, alum. Jotamastic 80 WG, alum. Jota Armour WG	150 150 <u>1000</u> <b>1300</b>	3410-12-006106 Mt01
4-5	Sa 2½	Penguard Universal Marathon 1000 GF Aggregates Marathon Deck Top	200 1300 1000 <u>500</u> <b>3000</b>	SL 16552-2
4-6	Sa 2½	Marathon 1000 GF Marathon 1000 GF Aggregates Marathon Deck Top	750 750 1000 <u>500</u> <b>3000</b>	SL 16553-2